



THE CARBON NANOTUBE SPECIALIST

NANO-ENGINEER YOUR FUTURE

PLASTICYL

Ref: PLASTICYL™ HDPE1501 – 05 March 2009 – V02

PLASTICYL™ HDPE1501 / Product Data Sheet

General information

Description

PLASTICYL™ is a family of Multi-Wall Carbon Nanotubes thermoplastic concentrate for applications requiring superior electrical conductivity and electrostatic discharge (ESD) property. Due to its high flow formulation PLASTICYL™ HDPE1501 is ideal for standard injection molding and extrusion process.

Applications

- ESD (Electrostatic Discharge) and electrically conductive parts
- E&E, Automotive, Industrials
- Injection molding, extrusion

Benefits

- Electrical conductivity at low loading
- Retention of key mechanical properties
- Easier Processing

Main characteristics

CARBONE NANOTUBES LOADING (% _{WT})	REAL DENSITY (G/L) ISO 1183	MFI (G/10 MIN) NON STANDARD TEST : 260 °C ; 20 KG ; 4 MM	MELTING POINT (°C) ISO 11357-1,-3
15 ± 1,0	977	7,84	135

Nanocyl S.A.

Rue de l'Essor 4
B-5060 Sambreville
BELGIUM

Tel +32 71 750 380
Fax +32 71 750 390
sales@nanocyl.com

US contact

info-us@nanocyl.com

www.nanocyl.com



THE CARBON NANOTUBE SPECIALIST

NANO-ENGINEER YOUR FUTURE

PLASTICYL

PLASTICYL™ HDPE1501 / Product Data / Page 2

Typical Performance data after dilution

	STANDARD	UNITS	NEAT POLYCARBONATE	DILUTION TO 2 % _{WT} OF CNT	DILUTION TO 4 % _{WT} OF CNT
<i>Melt flow index</i> (300 °C ; 1,2 kg* ; 2.160 kg**)	ISO 1133:1997	g/10 min	-	3,53*	1,97**

N.B.: Compounds were processed using a L/D ratio 48 twin-screw extruder using proprietary conditions

Important

This information is intended to be used only as a guideline for designers and users of modified thermoplastics. All information is believed to be accurate but is given without acceptance of liability. Users should make their own assessment of the suitability of the product for the purposes required. Properties may be materially affected by extrusion and molding parameters as well as by the shape and size of the part. No information supplied by Nanocyl constitutes a warranty regarding the product performance.

For technical assistance, sales or further information, please contact us :

Nanocyl S.A.

Rue de l'Essor 4 Tel +32 71 750 380
B-5060 Sambreville Fax +32 71 750 390
BELGIUM sales@nanocyl.com

US contact

info-us@nanocyl.com

www.nanocyl.com