



THE CARBON NANOTUBE SPECIALIST

NANO-ENGINEER YOUR FUTURE

PLASTICYL

Ref: PLASTICYL™ PC1501 – 03 March 2009 – V05

PLASTICYL™ PC1501 / Product Data Sheet

General information

Description

PLASTICYL™ is a family of Multi-Wall Carbon Nanotubes thermoplastic concentrate for applications requiring superior electrical conductivity and electrostatic discharge (ESD) property. Due to its low viscosity and high flow formulation PLASTICYL™ PC1501 is ideal for standard injection molding and extrusion process.

Key Applications

- E&E, automotives and packaging Industries
- HDD (hard disk drive) internal components
- HDD and IC handling trays

Benefits

- Excellent electrical conductivity at low loading
- Excellent surface cleanliness
- Retention of key mechanical properties
- Ease of processing

Main characteristics

CARBON NANOTUBES LOADING (% _{WT})	REAL DENSITY (G/L) ISO 1183	MFI (G/10 MIN) NON STANDARD TEST : 300°C ; 20 KG ; 4 MM
15 ± 1,0	1175	≤ 5,6

Nanocyl S.A.

Rue de l'Essor 4
B-5060 Sambreville
BELGIUM

Tel +32 71 750 380
Fax +32 71 750 390
sales@nanocyl.com

US contact

info-us@nanocyl.com

www.nanocyl.com



THE CARBON NANOTUBE SPECIALIST

NANO-ENGINEER YOUR FUTURE

PLASTICYL

PLASTICYL™ PC1501 / Product Data / Page 2

Typical Performance after injection molding

PROPERTIES	STANDARD	UNITS	NEAT POLYCARBONATE (MAKROLON® 2205)	DILUTION TO 2% _{WT} OF CNT	DILUTION TO 3 % _{WT} OF CNT
<i>Volume resistivity</i>	CTM E043	Ohm.cm	1.10^{13}	$1,2.10^3$	$5.40.10^1$
<i>Surface resistivity</i>	CTM E042	Ohm.sq	1.10^{15}	$1,70.10^4$	$1,2.10^3$
<i>Young modulus</i>	ISO 527-1,2	MPa	2141	2584	2683
<i>Tensile strength at break</i>	ISO 527-1,2	MPa	46	23	16
<i>Charpy notched impact strength</i>	ISO 180	kJ/m ²	31	10	6
<i>Melt flow index (300 °C ; 1,2 kg)</i>	ISO 1133:1997	g/10 min	38,6	16,9	0,9
<i>Burning behavior</i>	UL 94	Class	-	-	-

NB: Compounds were processed using a L/D ratio 48 twin-screw extruder using propriety conditions. Specimens were molded by injection, according to the processing parameters below.

General Processing guide for injection molding

INJECTION SPEED	MOLD TEMPERATURE	MATERIAL TEMPERATURE	PLASTICIZING SPEED	BACK PRESSURE	HOLDING PRESSURE	HOLDING TIME
<i>cm³/s</i>	°C	°C	<i>m/s</i>	<i>bars</i>	<i>bars</i>	<i>s</i>
30	120	300	0,4	40	450	8

Nanocyl S.A.

Rue de l'Essor 4
B-5060 Sambreville
BELGIUM


Tel +32 71 750 380
Fax +32 71 750 390
sales@nanocyl.com

US contact

info-us@nanocyl.com

www.nanocyl.com

Percolation Curves for volume and surface resistivity



NB: Electrical resistivity measurement in accordance to CTM E043 and CTM E402 (Cabot Testing Method), on standard injection molded IZOD specimens, processed according to parameters provided before (General Processing Guide for Injection Molding).

Important

This information is intended to be used only as a guideline for designers and users of modified thermoplastics. All information is believed to be accurate but is given without acceptance of liability. Users should make their own assessment of the suitability of the product for the purposes required. Properties may be materially affected by extrusion and molding parameters as well as by the shape and size of the part. No information supplied by Nanocyl constitutes a warranty regarding the product performance.

For technical assistance, sales or further information, please contact us :

Nanocyl S.A.

Rue de l'Essor 4 Tel +32 71 750 380
 B-5060 Sambreville Fax +32 71 750 390
 BELGIUM sales@nanocyl.com

US contact

info-us@nanocyl.com